

ARCHITECTURAL CONCRETE MASONRY

Product Specification Sheet

Architectural Concrete Masonry units shall meet the requirements of CAN3-A165

First Facet	Type	H - Hollow S - Solid
Second Facet	*Compressive Strength	H - 20 MPa S - 25 MPa
Third Facet (A)	Water Absorption	120 kg/m ³ (maximum)
Fourth Facet (M)	Moisture Content (% of total absorption) Identified as follows	40% (maximum) H/20/A/M S/25/A/M
Texture to be	(As Selected) Split Ashlar Split Fluted Split Centre Score	SRO SR8 SR2
Colour to be	(As Selected) Natural Grey Charcoal Red Tan Buff Bark Mottled	

Sizes As shown on the drawings.

*Also available in 30 MPa.

Architectural Block shall be as manufactured by Shaw Brick.

www.shawbrick.ca

PO Box 2130
Lantz, Nova Scotia, Canada, B2S 3G4
Tel: 902.883.2201 • Fax: 902.883.1457
email: salesinfo@shawbrick.ca

A MEMBER OF THE SHAW GROUP LIMITED

SHAW
B R I C K