



20 Clay Brick Way
Lantz, NS B2S 3G4
(902) 883-2201
salesinfo@shawbrick.ca
shawbrick.ca

Highland



Clay brick inspired by old Scotland, made right here in Atlantic Canada.

The Highland Collection brings the timeless warmth of tradition to your home with its distinctive blends of colours and textures. This collection features a growing design trend—blended bricks—that combine light golden tones with a subtle weathered effect for a naturally elegant look. The bricks' rich textures and gentle colour variations add depth and character, making them a perfect choice for creating a home with lasting charm and style.

COLOUR



Aberdeen



Argyll



Ayrshire



Blackburn



Braemore



Edinburgh



Glasgow



Kilwinning




Kirkhill




Stirling

SHAPE



Max 57



Metric
Modular

TEXTURE



Wirecut

ADDITIONAL INFORMATION/SPECIFICATIONS



20 Clay Brick Way
Lantz, NS B2S 3G4
(902) 883-2201
salesinfo@shawbrick.ca

BRICK MEASUREMENT CHART

Sizes	Metric	Imperial	Approximate Weight	Pieces per Pallet	Coverage
Modular	57 x 90 x 190 mm	2 1/4" x 3 1/2" x 7 5/8"	4 lbs	500	7 pieces/sq. ft.
Max 57	57 x 90 x 255 mm	2 1/4" x 3 1/2" x 10 1/8"	5 lbs	400	5.2 pieces/sq. ft.

Minimum Compressive Strength - Gross Area MPa (P.S.I.)

Red: 80-100 (11,000-14,000)

Brown: 70-90 (10,000-13,000)

Buff: 65-85 (9,500-12,000)

Maximum Water Absorption (24 hr. %)

Red: 1 - 3

Brown: 2 - 4

Buff: 6 - 8

Maximum Saturation Coefficient

Red: 0.65 - 0.78

Brown: 0.50 - 0.70

Buff: 0.70 - 0.78

Maximum Initial Rate of Absorption

Red: 1g/min/5,000mm

Brown: 5g/min/20,000mm

Buff: 10g/min/20,000mm

Freeze Thaw % After 50 Cycles - Meets Requirements