

OLDE ENGLISH WINCHESTER



Clay Brick with century-old warmth and character

The Olde English Collection of Clay Bricks from Shaw Brick evokes the warm feelings and character of century-old brick, yet - thanks to modern technology - offers the exceptional strength and durability of today.

Each Olde English brick emerges from the kiln uniquely textured and shaded with just the right amount of colour variation and distressed texture in the brick face. This Clay Brick Collection is available in two colours: Winchester and Essex.

150 years of brick design and quality innovation

While the look and feel might be Olde English, the actual brick is new through and through.

Manufactured right here in Atlantic Canada, Clay Brick from Shaw Brick has been a timeless staple of the construction industry for over 150 years. And, Shaw's Clay Brick is just as desirable now as it was a century and a half ago thanks to our continuous innovations in product design and quality.

Drop into a [Shaw Retail Centre](#) or one of our [independent dealers](#) to see samples of these bricks and learn more about any product in the Shaw Masonry Collection.

SPECIFICATIONS



20 Clay Brick Way

Lantz, NS B2S 3G4

(902) 883-2201

salesinfo@shawbrick.ca

Brick Measurement Chart

| Sizes | Metric | Imperial | Approximate Weight | Pc/Pallet | Coverage |
|---------|---------------|---------------------------|--------------------|-----------|--------------|
| Modular | 57x90x190mm | 2 ¼" x 3 ½" x 7 5/8" | 4lbs | 500 | 7 pcs/sqft |
| Saxon | 90x90x190mm | 3 ½" x 3 ½" x 7 5/8" | 6lbs | 305 | 4.9 pcs/sqft |
| Max 57 | 57x90x255mm | 2 ¼" x 3 ½" x 10 1/8" | 5lbs | 400 | 5.2 pcs/sqft |
| Ontario | 60x102x213mm | 2 3/8" x 4" x 8 3/8" | 5lbs | 395 | 6 pcs/sqft |
| CSR | 70x90x230 | 2 3/4" x 3 1/2" x 9 1/16" | 6lbs | 380 | 4.9 pcs/sqft |
| MAX | 79x90x290 | 3 1/8" x 3 1/2" x 10 1/8" | 7lbs | 276 | 3.9 pcs/sqft |
| Slender | 12.7x90x190mm | 1/2" x 3 1/2" x 7 5/8" | 28lbs/box | 34pcs/box | 7 pcs/ sqft |

Note: Not all bricks are available in all sizes as indicated. Please contact your Shaw Brick Sales Representative or email salesinfo@shawbrick.ca for minimum special order quantities and production lead times.

Clay Brick Product Specifications

| CSA STANDARD VS. SHAW – TYPICAL TEST REPORT | | | | |
|---|-----------------------------------|----------------------------|---------------------------|------------------------|
| Property | CSA Standard A82-06 | SHAW BRICK | | |
| | | Red | Brown | Buff |
| Minimum Compressive Strength Gross Area MPa (P.S.I.) | 20.68 (3,000) | 80 – 100 (11,000 – 14,000) | 70 – 90 (10,000 – 13,000) | 65-85 (9,500 – 12,000) |
| Maximum Water Absorption 24 hr. % | 8.0 | 1 – 3 | 2 – 4 | 6 – 8 |
| Maximum Saturation Coefficient | 0.78 | 0.65 – 0.78 | 0.50 – 0.70 | 0.70 – 0.78 |
| Maximum Initial Rate of Absorption | 30g/min/ 20,000mm ² | 1 – 5 | 5 – 20 | 10 – 20 |
| Freeze Thaw % After 50 Cycles | Less than 0.5% loss in dry mass | Meets Requirements | | |

To view more photos and for more information on this product, visit: shawbrick.ca/products/olde-english-winchester/