



20 Clay Brick Way
Lantz, NS B2S 3G4
(902) 883-2201
salesinfo@shawbrick.ca
shawbrick.ca

Tweedtex





20 Clay Brick Way
Lantz, NS B2S 3G4
(902) 883-2201
salesinfo@shawbrick.ca
shawbrick.ca

A classic clay brick with a distinctive vertical brushed finish.

Tweedtex Clay Brick offers a dependable, warm, and inviting feel, reminiscent of quality tweed or corduroy fabric. With its distinctive vertical brushed texture, this classic brick exudes a comforting sense of tradition and timeless appeal. A staple in Shaw's Clay Brick Collection for decades, Tweedtex combines enduring style with the reliability you expect in a premium building material.

COLOUR



Charcoal



Grey



Magnum
Brown




Mingled
Shade




Red

SHAPE



Max 57



Metric
Modular

TEXTURE



Brushface

SPECIFICATIONS



20 Clay Brick Way
Lantz, NS B2S 3G4
(902) 883-2201
salesinfo@shawbrick.ca

BRICK MEASUREMENT CHART

Sizes	Metric	Imperial	Approximate Weight	Pieces per Pallet	Coverage
Modular	57 x 90 x 190 mm	2 1/4" x 3 1/2" x 7 5/8"	4 lbs	500	7 pieces/sq. ft.
Max 57	57 x 90 x 255 mm	2 1/4" x 3 1/2" x 10 1/8"	5 lbs	400	5.2 pieces/sq. ft.

Note: Not all bricks are available in all sizes as indicated. Please contact your Shaw Brick Sales Representative or email salesinfo@shawbrick.ca for minimum special order quantities and production lead times.

Clay Brick Product Specifications

CSA STANDARD VS. SHAW – TYPICAL TEST REPORT				
Property	CSA Standard A82-06	SHAW BRICK		
		Red	Brown	Buff
Minimum Compressive Strength Gross Area MPa (P.S.I.)	20.68 (3,000)	80 – 100 (11,000 – 14,000)	70 – 90 (10,000 – 13,000)	65-85 (9,500 – 12,000)
Maximum Water Absorption 24 hr. %	8.0	1 – 3	2 – 4	6 – 8
Maximum Saturation Coefficient	0.78	0.65 – 0.78	0.50 – 0.70	0.70 – 0.78
Maximum Initial Rate of Absorption	30g/min/20,000mm ²	1 – 5	5 – 20	10 – 20
Freeze Thaw % After 50 Cycles	Less than 0.5% loss in dry mass	Meets Requirements		